

Technical Data Sheet



PROSATIN

This high performance 1K clear coat gives a satin clear finish with outstanding UV resistance. It that can be applied over all water and solvent based basecoats making it ideal for smart repairs.

Code - PROSATIN



proxl.com

Visit our website
for more products



Technical Data

Technical Information

Size	500ml
Basis of binder	Acrylic Resin
Gloss level	60 (60° to DIN 67530) A high air humidity can cause loss of gloss.
Theoretical Coverage	1.9 - 2.5m ² Depending on the colour of the base colour
Temperature resistance to	110°C
VOC Directive	2004/42/IIIB(e),(840)
VOC content	680.2 g/l
Storage stability	Store in a cool dry place in original container between -10°C & +25°C
Shelf Life	10 years if appropriate storage provided (=10°- 25°C, relative air humidity of max. 60%)

Substrates

- Solvent and water based basecoat paints

Surface Preparation

- 1 Carry out test spray
- 2 Areas to be sprayed must be free of grease, dust and dry.
- 3 Use ProCLEANER to clean surface before coating
- 4 For professional use only
- 5 Wear an appropriate respirator (recommended type A2/P3)

Drying time









(at 20°C, 50% relative air humidity):

Dust dry	5-10 mins
Touch-dry	10-20 mins
Hard dry	24 hrs
Re-Coatable	24 hrs
IR	15-20 mins

The drying time is depending on the ambient temperature, air humidity and the applied paint layer

Application Guide

For optimal coating results, bring can to temperature prior to use (20 - 25 °C) and a relative air humidity of 45 - 60%.

1 	Shake aerosol for at least two mins, after agitator ball is free
2 	Apply in cross coats from distance of 250mm from object
3 	Apply 2 - 3 coats. 40µm film thickness
4 	Allow 5 mins flash off
5 	20°C - 24 hours 60°C - 40 mins IR - 15 - 20 mins
6 	Infrared for 15 - 20 mins
7 	After use, turn aerosol upside down and empty valve
8 	Use ProBLEND or UltraBLEND to blend out between old and new finish

DISPOSAL

Completely emptied cans should be put in recycling skips or appropriate container. Cans which are not empty should be disposed of as special refuse.

This application and technical information is given to the best of our knowledge. The notes mentioned herein are, however, non-binding and do not exempt you from own tests to see whether the products supplied by us are suitable for your special application. The use and processing is beyond our control and therefore exclusively is the responsibility of the user.

ENVIRONMENTAL

ProXL is committed to use formulations without restricted or critical ingredients and to achieve the best possible performance. The caps and packagings are made of recyclable material.

DISCLAIMER OF LIABILITY

The information contained in this Technical Data Sheet is correct to the best of Alpha Coatings Limited trading as Capella Solutions Group's ("Capella") knowledge, however, you must satisfy yourselves that the Goods are suitable for your needs by way of your independent testing or other processes. Capella makes no warranty, representation, or guarantee regarding the information contained in the Technical Data Sheet or the suitability of its products and services for any particular purpose, nor does Capella assume liability arising out of the application or use of the Goods other than any liability which cannot be limited by law including but not limited to liability for: (a) death or personal injury caused by negligence; (b) fraud or fraudulent misrepresentation; and (c) breach of the terms implied by section 12 of the Sales of Goods Act 1979, in such circumstances Capella's total liability shall not exceed the cost of the Goods. Capella's total liability includes liability in contract, tort, negligence, breach of statutory duty, or otherwise. It is the Customer's responsibility to ensure that the guidance on the Technical Data Sheet is followed.